## Tred-MOR® Carpet Cushion

- Made of SYNTHETIC RUBBER
- ► Recommended for Double-Glue Installations in High-Traffic Areas

## **SPECIFICATIONS**

	Tred-MOR 1562®	Tred-MOR 2568®	Tred-MOR 2580®	Test Standard
Recommended Use:	Extra-heavy commercial. Includes institutional areas subject to CONTINUOUS rolling-wheel traffic.	Heavy commercial. Includes institutional areas subject to PERIODIC rolling-wheel traffic.	Extra-heavy commercial. Includes institutional areas subject to FREQUENT rolling-wheel traffic.	
Product Codes:	BV0170	BV0175	BV0179	
Composition:	100% Synthetic Rubber	100% Synthetic Rubber	100% Synthetic Rubber	
Thickness:	0.156"	0.250"	0.250"	ASTM D3574
Density:	33 lbs/ft³ or 62 oz/yd²	22 lbs/ft³ or 68 oz/yd²	26 lbs/ft³ or 80 oz/yd²	ASTM D3574
R-Value:	0.270	0.460	0.480	
Color:	Black	Black	Black	
Moisture Barrier:	StainSTOP™	StainSTOP™	StainSTOP™	
Backing Top/Bottom:	Non-Woven/Polytek	Non-Woven/Polytek	Non-Woven/Polytek	
Available with QuikLIFT® backing	N/A	Yes	N/A	
Commercial Traffic Class:	Class III Extra-Heavy	Class II Heavy	Class III Extra-Heavy	
Roll Size:	15 yd²	15 yd <sup>2</sup>	15 yd²	
Dimensions:	54" x 30'	54" x 30'	54" x 30'	
PERFORMANCE				
CLD psi @ 25% & 65% Deflec. Min:	7.0 & 45.0	3.0 & 20.0	5.0 & 25.0	Method 601/12151
Compression Set, Max %	15	17.5	15	ASTM D3676
Breaking Strength Length/ Width, Min. psi	45/41	45/41	45/41	ASTM D2646
ACOUSTICAL PROPERTIES				
Impact Insulation Class (IIC):	71	75	74	ASTM 492
Sound Absorption (NRC):	0.30	0.35	0.35	ASTM C423-81
FLAMMABILITY				
Pill Test:	Passes	Passes	Passes	DOC-FF 1-70
Smoke Density Test (NIST):	Passes	Passes	Passes	ASTM E662-97
Radiant Panel Test:	N/A – cushion	must be tested in combination	on with carpet	ASTM E648
PROTECTION				
Antimicrobial:	Guardian™	Guardian™	Guardian™	EPA-Registered
Hypoallergenic:	Yes	Yes	Yes	
Indoor Air Quality:	Certified	Certified	Certified	CRI Green Label Plus
Warranty:	Life of the Carpet	Life of the Carpet	Life of the Carpet	















